

Dislocation structure and kinetics in slip-twin model



Max-Planck-Institut
für Eisenforschung GmbH

MSU Twin Meeting, Duesseldorf – October 6th, 2009



Internal variables:

- N^α edge dislocation densities $\varrho_{\text{edge}}^\alpha$
- N^α dipole densities $\varrho_{\text{dipole}}^\alpha$

Derived measures:

- τ_c^α threshold shear stress
- λ^α mean distance between 2 obstacles seen by a dislocation



Threshold stress τ^α :

$$\tau_c^\alpha = G_{\text{iso}} b^\alpha \sqrt{\sum_{\tilde{\alpha}=1}^{N^\alpha} \xi^{\alpha\tilde{\alpha}} (\varrho_{\text{edge}}^{\tilde{\alpha}} + \varrho_{\text{dipole}}^{\tilde{\alpha}})}$$

with:

- G_{iso} Isotropic shear modulus
- b^α Burgers vector of slip system α
- $\xi^{\alpha\tilde{\alpha}}$ interaction strength (Kubin et al. 2008)



Orowan's kinetics

Shear rate $\dot{\gamma}^\alpha$:

$$\dot{\gamma}^\alpha = \varrho_{\text{edge}}^\alpha b^\alpha v_{\text{glide}}^\alpha$$

Velocity v_{glide}^α :

$$v_{\text{glide}}^\alpha = v_0 \exp \left[-\frac{Q}{k_B T} \left(1 - \left(\frac{|\tau^\alpha|}{\tau_c^\alpha} \right)^p \right)^q \right] \text{sign}(\tau^\alpha)$$

with:

- v_0 Velocity pre-factor
- Q Activation energy for dislocation glide
- $k_B T$ Boltzmann energy



Multiplication:

$$\dot{\varrho}_{\text{multiplication}}^{\alpha} = \frac{|\dot{\gamma}^{\alpha}|}{b^{\alpha} \lambda^{\alpha}}$$



Dipole formation:

$$\dot{\varrho}_{\text{formation}}^{\alpha} = 2 \frac{\hat{d}^{\alpha}}{b^{\alpha}} \frac{\varrho_{\text{edge}}^{\alpha}}{2} |\dot{\gamma}^{\alpha}|$$

Length \hat{d}^{α} :

$$\hat{d}^{\alpha} = \frac{1}{8\pi} \frac{G_{\text{iso}} b^{\alpha}}{1-\nu} \frac{1}{|\tau^{\alpha}|}$$



Single-single annihilation:

$$\dot{\varrho}_{\text{single-single}}^{\alpha} = 2 \frac{\check{d}^{\alpha}}{b^{\alpha}} \frac{\varrho_{\text{edge}}^{\alpha}}{2} |\dot{\gamma}^{\alpha}|$$

Length \check{d}^{α} :

$$\check{d}^{\alpha} \propto b^{\alpha}$$

Spontaneous annihilation of one single dislocation and one dipole constituent



Single-dipole constituent annihilation:

$$\dot{\varrho}_{\text{single-dipole}}^{\alpha} = 2 \frac{\check{d}^{\alpha}}{b^{\alpha}} \frac{\varrho_{\text{dipole}}^{\alpha}}{2} |\dot{\gamma}^{\alpha}|$$



Dipole climb:

$$\dot{\varrho}_{\text{climb}}^{\alpha} = \varrho_{\text{dipole}}^{\alpha} \frac{4 v_{\text{climb}}}{\hat{d}^{\alpha} + \check{d}^{\alpha}}$$

Climb velocity $v_{\text{climb}}^{\alpha}$:

$$v_{\text{climb}}^{\alpha} = \frac{D \Omega^{\alpha}}{b^{\alpha} k_B T} \frac{G_{\text{iso}} b^{\alpha}}{2 \pi (1 - \nu)} \frac{2}{\hat{d}^{\alpha} + \check{d}^{\alpha}}$$



Edge dislocation density rate:

$$\dot{\varrho}_{\text{edge}}^{\alpha} = \dot{\varrho}_{\text{multiplication}}^{\alpha} - \dot{\varrho}_{\text{formation}}^{\alpha} - \dot{\varrho}_{\text{single-single}}^{\alpha}$$

Dislocation dipole density rate:

$$\dot{\varrho}_{\text{dipole}}^{\alpha} = \dot{\varrho}_{\text{formation}}^{\alpha} - \dot{\varrho}_{\text{single-dipole}}^{\alpha} - \dot{\varrho}_{\text{climb}}^{\alpha}$$